# **TECHNICAL DATA SHEET**

Date of Issue: 2017/09/06

# iso-Propylmagnesium Chloride, typ. 20 % solution in THF (typ. 1.9 M)

CAS-No. 1068-55-9

EC-No. 213-947-1

REACH No. 01-2119919043-47

Molecular Formula C<sub>3</sub>H<sub>7</sub>ClMg

Product Number 408483

APPLICATION Grignard-reactions: reagent for the introduction of the iso-propyl group.

FURTHER INGREDIENTS

Tetrahydrofuran

CAS-No. 109-99-9 EC-No. 203-726-8

**SPECIFICATION** 

iso-Propylmagnesium Chloride: 19.0 - 21.0 %

## METHOD OF ANALYSIS

Determination of assay as total base by acidimetric titration after hydrolysis; detailed description available on request.

## PHYSICAL PROPERTIES

Appearance liquid

Color yellowish to brown

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.



MgCl

Product Number: 408483 Date of Issue: 2017/09/06

Crystallization temperature

ca. 5 °C

Flash point

-27.0 °C 1,013.3 hPa

Boiling point/boiling

62.4 °C at 899.8 hPa

range

Method: OECD Test Guideline 103

Density

0.97 g/cm3 at 20 °C Method: OECD Test Guideline 109

Water solubility

(Not applicable)

Molecular weight

102.85 g/mol

Thermal Stability

crystallisation below around 5 °C

#### HANDLING & STORAGE

Handling Organomagnesium compounds should only be handled under inert gas (nitrogen or

argon). Never add water, acids or oxidizing materials to the product. In case of fire use dry extinguishers on basis of sodium chloride or limestone powder. Never use water or CO2-extinguishers. Pay attention to official safety regulations (see also:

"Transport regulations" and "GHS Hazard Pictograms").

Storage Under exclusion of air and humidity stable over practically unlimited periods. As


material tends to crystallize at lower temperatures, it should be stored above 10 °C. Precipitates can be redissolved by warming and appropriate homogenization. Keep

container dry and tightly closed.

#### TRANSPORT & PACKAGING

#### UN number 3399

ADR	Class: 4.3	PG: I	Label: 4.3 (3)
RID	Class: 4.3	PG: I	Label: 4.3 (3)
IMDG	Class: 4.3	PG: I	Label: 4.3 (3)
IATA_C	Class: 4.3	PG: I	Packing instruction (cargo aircraft): 494
IATA_P	Class: 4.3	PG: I	





Product Number: 408483 2017/09/06 Date of Issue:

#### Hazard pictograms









Signal Word Danger

**H&P Phrases** See Safety Data Sheet

The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary Labelling

in other countries. Please refer to the respective Safety Data Sheet for your country.

## Packaging

Glass bottles of 100, 250, 500 and 1,000 ml. Steel bottles with volumes of 7.4, 27, 127 or 450 l. For safety reasons these are filled to a maximum of 90 %. Steel drums up to 200 l.

#### OTHER INFORMATION

**Further Related** 

Safety Data Sheet

**Documents** 

Organomagnesium Compounds Our brochure(s)

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

